

# Product Specification: Stawell Quarry 40mm Post Primary Crushed Rock

**PRODUCT CODE:** 0232

**SOURCE ROCK TYPE:** Hornfels

**CUSTOMER:** Standard Product

**REFERENCE:** Conundrum historical data


Relevant Tests Carried Out On Source Rock				
Test	Method	Frequency	Requirements	Reference
Nil	N/A	N/A	N/A	N/A

## Tests Carried Out For Product Quality Control Purposes

Sampling Method: AS1141.3.1

Test	Method	Frequency	Requirements	Reference
Unit Mass Density	AS1141.4	On initial introduction of product	N/A - For reference purposes only	N/A
Maximum Dry Density / Optimum Moisture Content	AS1289.5.2	1 per 3 Years	N/A - For reference purposes only	N/A
Plastic Index (PI)	AS1289.3.3.1	1 per 3 Years	N/A - For reference purposes only	N/A
Liquid Limit (as part of PI test)	AS1289.3.3.1	1 per 3 Years	N/A - For reference purposes only	N/A
Particle size distribution (Grading)	AS1141.11 (washed)	1 per Year	N/A - Data below for reference purposes only	Conundrum historical data

Sieve Size AS (mm)	Limits of Grading (% Passing)	Target Grading (% Passing)
53.0	100	100
19.0	60 – 95	80
0.425	7 – 40	24
0.075	2 – 25	15



Date issued: 29 Aug 2006  
 Issue number: 2  
 Authorised by: Tom Kerr  
 Date printed: 7 Aug 2009

Previous issue date: 9 May 2002

Date of first issue: 9 May 2002  
 Max review interval: 5 years  
 Manual index location: 19.i  
 Form: 2032.02