

# Product Specification: Stawell Quarry 5mm Class A Aggregate

**PRODUCT CODE:** 0247

**SOURCE ROCK TYPE:** Hornfels

**CUSTOMER:** Standard Product

**REFERENCE:** *VicRoads Standard Specifications for Road works and Bridgeworks, Sections 801 & 831*

Relevant Tests Carried Out On Source Rock				
Test	Method	Frequency	Requirements	Reference
Los Angeles (LA) Value	AS1141.23	VicRoads Issue	≤20	VicRoads 801.033
Polished Stone (PS) Value	RC374.01	VicRoads Issue	≥48	VicRoads 801.034
Preparation of Reference Specimens	AS1141.30 Appendix A	VicRoads Issue	See below for sound and marginal classifications	VicRoads 801.04
Degradation Factor – Source Rock	AS1141.25.1	VicRoads Issue	Sound ≥40% Marginal 20-39%	VicRoads 801.031 & 801.032

Tests Carried Out For Product Quality Control Purposes				
Sampling Method: AS1141.3.1				
Test	Method	Frequency	Requirements	Reference
Unit Mass Density	AS1141.4	1 per 3 Years	N/A - For reference purposes only	N/A
Unsound stone count by visual assessment	AS1141.30 / RC372.01	1 per 500t	Unsound ≤5% Marginal + Unsound ≤10%	VicRoads 831.051
Particle size distribution (Grading)	AS1141.11 (washed)	1 per 500t	See table below	VicRoads 831.05.e

Sieve Size AS (mm)	Limits of Grading - Individual test		Limits of Grading - Mean of lot		Target Grading (% Passing)
	(% Passing)	(% Retained)	(% Passing)	(% Retained)	
6.70	100	-	100	-	100
4.75	80 – 100	-	85 – 100	-	>90
2.36	-	55 (min)	-	60 (min)	<15
1.70	0 – 15	-	0 – 10	-	<4
0.600	0 – 3	-	0 – 2	-	<1

Date issued: 25 Oct 2006  
Issue number: 3  
Authorised by: Tom Kerr  
Date printed: 7 Aug 2009

Previous issue date: 28 Aug 2006

Date of first issue: 9 May 2002  
Max review interval: 5 years  
Manual index location: 19.i  
Form: 2047.02