

Product Specification:

Wim Mix Pre-Mixed Concrete – 45 MPa, 14mm Maximum Agg. Size

PRODUCT CODE: 110-108-m **NOMINAL STRENGTH:** 45 MPa **GRADE DESIGNATION:** S45

CUSTOMER: Standard Product

REFERENCE: AS1379 – *Specification and Supply of Concrete*

Compliance Requirements for Product Constituents	
Constituent	Compliant With
14/10mm G Agg	AS 2758.1
7mm SS Agg	AS 2758.1
Coarse Sand	AS 2758.1
Fine Sand	AS 2758.1
GP Cement	AS 3972
Mixing Water	AS 1379
Chemical Admixtures	AS 1487

Tests Carried Out For Production Control (Associated Grade)					
Test	Sample Method	Test Method	Frequency	Requirements	Reference
Slump	AS1012.1	AS1012.3	1 per 100m ³	As per AS1379: Table 6	AS1379.5.2
28-day Strength	AS1012.1	AS1012.9	1 per 100m ³ (2 cylinders)	Mean (f_{cm}) $\geq f_c + k_{cs}$ 95% of results ≥ 45 MPa	N/A
7-day Strength	AS1012.1	AS1012.9	1 per 100m ³	Mean for production interval ≥ 23 MPa	N/A
Air Content	AS1012.1	AS1012.4.2	On every second strength sample as required by customer	$\pm 1.5\%$ of customer's specified air content	AS1379.5.4

Date issued: 7 Aug 2009
Issue number: 2
Authorised by: Tom Kerr
Date printed: 7 Aug 2009

Previous issue date: 21 Feb 2007

Page 1 of 1

Date of first issue: 21 Feb 2007
Max review interval: 5 years
Manual index location: 19.i
Form: 2000.11.S45-14